

Arena Wood Floor Coating

arena™ 200



A low VOC, quick-dry wood floor coating with exceptional durability and shine

Features

- 100% urethane, water-based OMU (oil-modified urethane) wood floor coating
- Very mild scent
- Single component, no mixing
- Easy application
- Excellent adhesion
- High gloss
- Quick dry time
- Greater abrasion resistance

Advantages

- Environmentally safer - VOC compliant
- No solvent odor
- No mixing required
- Excellent leveling
- Quicker recoat

Available in:



4x1
Gallon
Cases



5-gallon
Action
Pacs®

Coverage:

- 600-700 square feet per gallon
- 4 to 16-hour recoat window after tack-free

Additional Products:

- Buckeye Green Light™ Super Concentrated Floor Cleaner
- Floortonic™ Burnishing Liquid

Other Equipment needed:

- Low-speed, single disc floor machine (175 rpm) with 20-inch, #120 or #150 grit screens (depending on floor inspection)
- 24-inch or 36-inch push broom (for sweeping and tacking)
- Terry cloth towels for tacking
- Putty knife or scraper
- Lightweight T-bar (18", 24", or 30")

Preparation:

Apply Arena 200 only when temperature is between 65°F and 95°F, and humidity is under 80%. Substrate and product must also be acclimated.

Follow MFMA and NOFMA guidelines for wood acclimation time prior to installation, sanding, and coating.

Note:

Do not use Steel Wool Pads in preparation or application. Steel fibers that remain on the floor will rust when coated.

DIRECTIONS

This product is designed to be used as is (DO NOT DILUTE). Thinning or reducing with solvents is not recommended.

Previously coated floors:

It is strongly recommended to test a small area first for adhesion purposes over a previous water-based or unknown coating.

Note: Do not use **Arena 200** on solvent stained wood unless the stain has been sealed.

1. Remove all tape and gum with a putty knife or scraper. Then clean the floor with **Tenacity®** if floor is extremely dirty.
2. Let floor dry completely.
3. Screen floors using #120 or #150 grit screens (200 sq.ft per side) using **Screen Clean™** Ready-To-Use Floor Prep Cleaner until gloss is removed.
4. Scrub/rinse floor with autoscrubber and red or blue pads.
5. Tack rag floor with water.
6. Continue on to Coating section.

For instructions on newly installed floors, sanded to bare wood floors, and applying sealer, please contact your Buckeye sales representative or the Buckeye Research department.

Complete line painting after floor preparation and before applying coats of **Arena 200**. Consult a Buckeye representative for painting instructions.

Note: Test paint before using.

Coating:

1. Apply **Arena 200** with a lightweight T-bar applicator going with the grain. Do not puddle coating.

2. Let floor dry approximately 2 hours to tack-free. Then allow at least an additional 4 hours but no more than 16 hours after tack-free before recoating.
Note: Abrade floor with a maroon pad if cured more than 16 hours but not more than 72 hours. Do not use a screen.
3. Apply next coat of **Arena 200**.
4. Close doors and windows, and turn off vent fans and air conditioning fans to avoid excess and directed air while coating.

Clean-Up and Curing:

1. Clean tools, equipment and work area with water.
2. Let floors cure for 48 hours after last coat before allowing light traffic, and 2-5 days before sports play.

Adequate ventilation is imperative during curing time. Dry times will vary based on conditions.

Maintenance:

1. Dust mop the floor daily.
2. Use **Buckeye Green Light™** to remove tough soils/dirt. Follow directions on label.
3. Keep shoe traffic limited by placing walk-off mats at all entrances to prevent dirt from tracking onto the floor, and keep mats clean. Be mindful not to drag tables/chairs across the floor, which may cause floor damage.

Troubleshooting

Slow dry – low curing temperatures, high humidity, air movement, or lack of ventilation after application

Streaks – result when coating is applied too thin

Fisheyes – foreign material on the surface such as oil, grease, or silicone

Bubbling – results when coating is overworked with the applicator including shaking the coating before application or high temperatures during application

Peeling – improper floor prep

Dirt particles – result when the applicator is not “de-fuzzed” causing loose fibers in the film or when the room vents are not sealed off during application

Screen marks – result when an overly-aggressive screen is used between coats

Hazy film – results when there is high humidity during drying

Steel Wool Pads - Do Not Use. Steel fibers will remain in the floor and will rust when coated.

String mops – Do Not Use. Mops apply unevenly and leave behind swirl marks.

Air Movement – Close all doors, windows, and turn off vent fans and AC fans.

Premature curing can occur, disrupting flow and leveling

Stained wood – Do Not Use **Arena 200** over solvent stained wood unless it has already been sealed

Technical Specifications:

| | |
|--------------------|--------------------|
| Color | Off-White |
| pH | 8.4 ± 0.2 |
| Weight/Gallon | 8.5 lbs. |
| Solids | 21 ± 1% |
| VOC | <44 g/L |
| Fragrance | Bland |
| Flash Point | None |
| Freeze Stability | Keep from freezing |
| Alcohol Resistance | Excellent |
| MFMA | Approved |